

SR.P200™


TYPE 2 EXPANDED POLYSTYRENE RIGID INSULATION

The SR.P200™ panels manufactured by Styro Rail Inc. are composed of type 2 expanded polystyrene [EPS] rigid insulation.

Available option:

SR.P200G™ panels manufactured with graphite polystyrene.

+ CHARACTERISTICS	
SR.P200™:	INSULATING VALUE OF RSI 0.70/25 MM [R-VALUE 4.0/INCH]
SR.P200G™:	SUPERIOR INSULATING VALUE WITH GRAPHITE : RSI 0.84/25 MM [R-VALUE 4.75/INCH]
MEETS CURRENT BUILDING CODE REQUIREMENTS	
CLOSED CELL- MOISTURE RESISTANT	
NON VAPOUR BARRIER	
PERMANENT R-VALUE – DOES NOT DIMINISH WITH TIME	
MEETS CAN/ULC-S701.1 STANDARD	



SR.P200™ **TYPE 2 EXPANDED POLYSTYRENE RIGID INSULATION**

AVAILABLE DIMENSIONS

				SR.P200™ REGULAR	SR.P200G™ GRAPHITE
610 mm x 2438 mm	[24" x 96"]	25 mm	[1"]	R4.0*	R4.8
1219 mm x 2438 mm	[48" x 96"]	32 mm	[1-1/4"]	R5.0*	R5.9
1219 mm x 2743 mm	[48" x 108"]	38 mm	[1-1/2"]	R6.0*	R7.1
1219 mm x 3048 mm	[48" x 120"]	44 mm	[1-3/4"]	R7.0	R8.3
		48 mm	[1-7/8"]	R7.5*	R8.9
		51 mm	[2"]	R8.0*	R9.5
		64 mm	[2-1/2"]	R10.0*	R11.9
		76 mm	[3"]	R12.0*	R14.3
		102 mm	[4"]	R16.0	R19.0
		127 mm	[5"]	R20.0	R23.8

Other dimensions available upon request. Square joints by default. Panels of 25 mm [1"]: ship lap joints available on two sides. Panels of 38 mm [1-1/2"] or more: ship lap joints available on two or four sides; G-Lock™ system available on two or four sides for 1219 mm [48"] wide panels.

* In stock

RECOMMENDED USE

SR.P200™ panels are the most versatile and can be used in many applications, both exterior and interior, above or below ground level. Install SR.P200™ panels on the interior and exterior surface of foundation walls, the interior and exterior surface of the framework, underneath the basement finished concrete slab and concrete slab of residential garages, flat and cathedral ceilings as well as flat and sloped roofs in order to obtain a continuous thermal envelope. Also used to insulate the underground drainage pipes, under landscape areas without vehicule circulation. Ideal for insulating underneath the basement finished concrete slab.

Install SR.P200G™ panels when a superior insulation value is needed for a specified thickness.

CERTIFICATION

Warnock Hersey has certified the type 2 expanded polystyrene contained in SR.P200™ and SR.P200G™ panels in accordance with the CAN/ULC-S701.1 standard. The type 2 expanded polystyrene produced by STYRORAIL™ is listed in the CCMC Registry of Product Evaluation under CCMC 13271-L.

SR.P200™ **TYPE 2 EXPANDED POLYSTYRENE RIGID INSULATION**

PHYSICAL PROPERTIES

INSULATING PANEL	SR.P100™	SR.P200™	SR.P300™	SR.P350™	SR.P400™	SR.P600™
Type	1	2	3	3	3	3
Thermal Resistance Min. Regular [ASTM C518] Thickness of 25 mm [1"]	RSI 0,65 [R3.7]	RSI 0,70 [R4.0]	RSI 0,74 [R4.2]	RSI 0,76 [R4.3]	RSI 0,76 [R4.3]	RSI 0,81 [R4.6]
Thermal Resistance Min. Graphite [ASTM C518] Thickness of 25 mm [1"]	RSI 0,83 [R4.7]	RSI 0,84 [R4.75]	RSI 0,85 [R4.8]	RSI 0,85 [R4.8]	RSI 0,85 [R4.8]	N/A
MVTR Max. [ASTM E96]	300 ng/Pa-s-m ² [5.24 US Perms]	200 ng/Pa-s-m ² [3.5 US Perms]	130 ng/Pa-s-m ² [2.27 US Perms]	130 ng/Pa-s-m ² [2.27 US Perms]	130 ng/Pa-s-m ² [2.27 US Perms]	130 ng/Pa-s-m ² [2.27 US Perms]
Compressive Strength Min. [ASTM D1621] 10% Deformation	70 kPa [10 PSI]	110 kPa [16 PSI]	140 kPa [20 PSI]	210 kPa [30 PSI]	276 kPa [40 PSI]	414 kPa [60 PSI]
Flexural Strength Min. [ASTM C203]	170 kPa [25 PSI]	240 kPa [35 PSI]	300 kPa [44 PSI]	345 kPa [50 PSI]	414 kPa [60 PSI]	517 kPa [75 PSI]
Water Absorption Max. [ASTM D2842] Volume	4 %	3 %	2 %	1.8 %	1.5 %	0.7 %
Dimensional Stability Max. [ASTM D2126] Linear Variation	1.5 %	1.5 %	1.5 %	1.5 %	1.5 %	1.5 %
Limiting Oxygen Index Min. [ASTM D2863]	24 %	24 %	24 %	24 %	24 %	24 %
Density Min. [ASTM C303]	16 kg/m ³ [1.0 lbs/ft ³]	20 kg/m ³ [1.2 lbs/ft ³]	25 kg/m ³ [1.5 lbs/ft ³]	29 kg/m ³ [1.8 lbs/ft ³]	39 kg/m ³ [2.4 lbs/ft ³]	53 kg/m ³ [3.3 lbs/ft ³]
Flame Spread Rating Regular [CAN/ULC S102.2]	145	145	145	145	145	145
Flame Spread Rating Graphite [CAN/ULC S102.2]	240	240	240	240	240	N/A

SR.P200™

TYPE 2 EXPANDED POLYSTYRENE RIGID INSULATION

ENVIRONMENTAL DATA

The expanded polystyrene used in the making of the SR.P200™ and SR.P200G™ panels are composed of 98% air and 2% plastic material.

They are manufactured without HCFC, HFC gases and without HBCD flame retardant.

The STYRORAIL™ products can contribute to LEED credits.

Please send us your LEED Material Declaration Form at projtleed@styorail.ca.

STORAGE

Store SR.P200™ and SR.P200G™ panels in a dry and ventilated location, protected from the outside elements, ultraviolet rays, open flames or other sources of ignition. Stack panels on pallets of minimum 100 mm [4"] over the ground.

Pay special attention to the storage of the SR.P200G™ panels made with graphite polystyrene.

Cover the unwrapped SR.P200G™ panels or if packaging has been damaged with an **opaque** white tarp. An excessive heat accumulation can deform products made with graphite polystyrene.

Do not store the SR.P200G™ panels near any reflective surfaces [ex: glass, metal]. A heat concentration from reflected sunlight can deform products made with graphite polystyrene.

INSTALLATION

Panels must be dry and in good condition before installation.

To limit the color loss from UV exposure, cover the installed SR.P200™ panels with an exterior cladding protecting them from ultraviolet rays.

Avoid the prolonged exposure to sunlight of the SR.P200G™ grey/black surface made with graphite polystyrene. Avoid the concentration of sunlight rays from radiation. Cover as soon as possible on hot days and/or during non-windy conditions. An excessive heat accumulation can deform products made with graphite polystyrene.

Refer to the *Installation Guide* for more information.

LIMITATIONS

Expanded polystyrene is combustible. Even if expanded polystyrene contains a flame retardant, limit use of open flame or ignition sources near product.

A protective barrier or thermal barrier is required as specified in the appropriate building code.

Expanded polystyrene may be affected by some oil based solvents.

An excessive heat accumulation can deform products made with graphite polystyrene.

EXEMPTION OF LIABILITY

The information herein is based on the present state of our best scientific and practical knowledge. The user is responsible for checking the suitability of products for their intended use. STYRORAIL™ technical data sheets are updated on a regular basis; it is the user's responsibility to obtain and to confirm the most recent version. Information contained in this data sheet may change without notice.